

SINTERING-DATA-SHEET

DR. FRITSCH GmbH & Co. KG

Dieselstraße 8

70736 Fellbach

Tel. 0711-518320; Fax 0711-5183210

powder - code:	V16-1117
-----------------------	----------

main component:	Fe	binder:	2 % alcohol	date:	12.12.2017
machine type:	DSP-25	aver. Grain size		testperson:	OE
utilisation:	Concrete and hard natural stone				

heating by	die:	X	temperature measure-	pyroscope:	
	punches:		ment by:	thermocouple:	X


temperature:	$^{\circ}C$	660	700	740	780	820	860	900	940
specific pressure:	N/mm^2	35	==>						
sintering time:	min	3	==>						

bending strength:	N/mm^2								
stretch at break:	$\%$								
average hardness:	HRB	79	96	96	103	106	106	109	109
hardness scattering:	HRB	76-81	95-97	87-99	102-104	104-107	105-107	106-110	108-110
average hardness:	HRC								
hardness scattering:	HRC								
weight:	g	17	==>						
weight after sintering:	g								

Volume ($V = G_s - G_w$)	cm^3								
Density ($D = G_s / V$)	g/cm^3	6,96	7,41	7,57	7,63	7,63	7,63	7,63	7,63

weight loss ($G = G_e - G_s$)	g								
rel. Weight loss ($Gr = G * 100$)	$\%$								

notes:									
---------------	--	--	--	--	--	--	--	--	--



Attention:

Depending on mould-geometry and type and place of temperature-measurement an increase up to 60 °C must be done to get the same result !
 In case of moulds with a high number of graphite punches a certain friction value needs to be considered. To obtain the detailed formula you are welcome to contact us.

Property of Dr. Fritsch GmbH & Co.KG. Transmission only allowed in explicit agreement with the management.